




## LISTING INFORMATION OF

Fibergrate - Firewalk Safe-T-Span Pultruded Grating

SPEC ID: 70101

Fibergrate Composite Structures, Inc. 900 FM 205 Stephenville, TX 76401 United States

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.



## LISTING INFORMATION

Firewalk Safe-T-Span Pultruded Grating is a light weight, corrosion resistant FRP composite grating manufactured with phenolic resin and engineered to meet the full requirements of ASTM F3059. It is commonly used for flooring, platforms and walkways where resistance to high temperatures and low smoke emissions is required. Firewalk grating is also designed for use in areas where conventional metallic grating would be subject to corrosion or impose a weight penalty

Firewalk Safe-T-Span Pultruded Grating is currently approved to ASTM F3059 at a thickness of 1.5-in. and bar spacing range of 1-in. to 1.5-in. on center.

## **FIRE RATINGS**

Standard	Rating
ASTM F3059, Section 17 Fire Integrity	Level 2
	Maximum clear span 44" (1118 mm)
ASTM F3059, Section 16 Surface Flammability	Flame Spread Index ≤ <b>20</b>
(ASTM E84)	Smoke Developed Index ≤ <b>450</b>

## **MATERIAL RATINGS**

Standard	Rating
ASTM F3059, Section 8 Deflection Limits	Met the requirements
ASTM F3059, Section 9 Assembled Grating Ultimate Failure	Met the requirements
ASTM F3059, Section 10 Wheel Loading	Met the requirements
ASTM F3059, Section 11 Assembled Panel Impact Resistance	Met the requirements
ASTM F3059, Section 12 (ASTM D2047)	Met the requirements
ASTM F3059, Section 13 (ASTM D4060)	Met the requirements
ASTM F3059, Section 14 (ASTM D4329)	Met the requirements
ASTM F3059, Section 15 Saltwater Spray Test (ASTM B117-19)	Met the requirements


Attribute Value

Criteria ASTM F3059 (2018)

CSI Code 06 82 00 Glass-Fiber-Reinforced Plastic

Intertek Services Certification
Listed or Inspected LISTED

Listing Section BUILDING MATERIALS WITH SURFACE BURNING CHARACTERISTICS



Spec ID 70101